

Eurofins Product Testing A/S Smedeskovvej 38 DK-8464 Galten Denmark

Tel. +45 70 22 42 76 Fax +45 70 22 42 75 voc@eurofins.dk www.eurofins.com/product-emissions Date 31 August 2015 Our ref. G22816B_05

Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

Sample material

BASF Construction Solutions GmbH

Dr. - Albert-Frank-Str. 32

83308 Trostberg Germany

Sample identification	MasterFlow 920 AN			
Product type	Multipurpose Construction Adhesive			
Product data, according to manufacturer	Density: 1.69 g/ml at 20 °C ** Water content: 4.9 g/l** Exempt compounds: none ***			
Date received	14.05.2013			
Analytical period	03.06.2013			

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty, U _m (%)			
LEED 2009 EQ c4.1	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %			
ASTM D 2369 - 10	accords was determined are vimetrically by besting up to 110 °C during 60 minute						
Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:							
([g all volatiles] - [g water] - [g exempt compounds]) / ([I material] - [I water] - [I exempt compounds])							

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, see also <u>www.eurofins.dk/uncertainty</u>.

Analytical results

	Solid content, % mass	Water content, % mass	Exempt com- pounds, % mass	VOC less wa- ter less ex- empt com- pounds, g/l	VOC limit g/l
MasterFlow 920 AN	97.4	0.3**	0***	39	70*

* VOC limit for "Multipurpose Construction Adhesives"

** Given by the client

*** No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Thomas Bjerring Analytical Service Manager

Maria Pello

Maria Pelle Chemist

The test results relate only to the items tested. The report shall not be reproduced except in full without the written approval of the testing laboratory.