

BASF Construction Solutions GmbH
 Dr. -Albert-Frank-Str. 32
 83308 Trostberg
 Germany

Eurofins Product Testing A/S
 Smedeskovvej 38
 8464 Galten
 Denmark

voc@eurofins.com
www.eurofins.com/voc-testing

Date
 31/08/2015


VOC Emissions Test report

1. Sample Information

Sample identification	MasterFlow 916 AN
Product type	Chemical anchor
Batch no.	46892
Production date	13/06/2012
Date when sample was received	09/07/2012
Testing (start - end)	10/07/2012 - 07/08/2012

2. Resulting VOC Emissions Class Label

This recommendation is based on French regulation as published on 25 March 2011 (décret DEVL1101903D) and on 13 May 2011 (arrêté DEVL1104875A). For details please see www.eurofins.com/france-voc



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

3. Conclusion on CMR emissions

The tested product fulfills the requirements of the French regulation DEVP0908633A of 30 April 2009 and DEVP0910046A of 28 May 2009. For details please see www.eurofins.com/france-voc.

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entity, parts of it only with a written acceptance by Eurofins.

4. Test Method

Method	Principle	Parameter	Quantification limit	Uncertainty	
ISO 16000 parts -3, -6, -9, -11 Internal method numbers: 9810, 9811, 9812, 2808, 8400	GC/MS HPLC/UV	VOC Volatile aldehydes	2 µg/m ³ 3 µg/m ³	22% (RSD)	
ISO 16000 parts -3, -6, -9, -11 Internal method numbers: 9810, 9811, 9812, 2808, 8400, 2616	HPLC/UV	4CMR	<1 µg/m ³	Um = 2 x RSD=45 %	
Test chamber parameter					
Chamber volume, l	119	Temperature, °C	23	Relative humidity, %	50
Air change rate, 1/h	0.5	Loading ratio(m ² /m ³)	0.007		
Test condition: Sample stayed in test chamber during the whole 28 days testing period.					
Sample preparation					
Thickness, mm	3				

5. Results

	Concentration after 28 days $\mu\text{g}/\text{m}^3$	C	B	A	A+
TVOC	< 2	>2000	<2000	<1500	<1000
Formaldehyde	< 4	>120	<120	<60	<10
Acetaldehyde	< 4	>400	<400	<300	<200
Toluene	< 2	>600	<600	<450	<300
Tetrachloroethylene	< 2	>500	<500	<350	<250
Ethylbenzene	< 2	>1500	<1500	<1000	<750
Xylene	< 2	>400	<400	<300	<200
Styrene	< 2	>500	<500	<350	<250
2-Butoxyethanol	< 2	>2000	<2000	<1500	<1000
Trimethylbenzene	< 2	>2000	<2000	<1500	<1000
1,4-Dichlorobenzene	< 2	>120	<120	<90	<60
CMR compounds		Maximum allowed air concentration			
Benzene	< 1			<1	
Trichloroethylene	< 1			<1	
Dibutylphthalate (DBP) *	< 1			<1	
Diethylhexylphthalate (DEHP) *	< 1			<1	

< Means less than

> Means higher than

* Not a part of our accreditation (EN ISO/IEC 17025:2005) by DANAK (no. 522))



Thomas Bjerring
Analytical Service Manager



Maria Pelle
Chemist

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.